

Exact Density of States in a System of Disordered Two Dimensional Dirac Fermions in the Unitarity Limit: The d-wave Superconductor

Catherine Pépin and Patrick A. Lee

Department of Physics, Massachusetts Institute of Technology, Cambridge, MA 02139

(February 1, 2008)

In this paper we present a method to compute the exact density of states induced by N non magnetic impurities in a system of two dimensional Dirac fermions in the unitarity limit. We review the case of the π -flux phase of the Heisenberg model and also treat the disordered d-wave superconductor. In both case we find additional states in the gap with $\delta\rho(\omega) \simeq n_i / |\omega (\ln^2 |\omega/\Delta_0| + (\pi/2)^2)|$.

As a consequence of the breakdown of Anderson's theorem [1], when impurity scattering violates the symmetry of the superconducting state, the superconducting energy gap is depleted and impurities act as strong pair breakers. This is the case in s-wave superconductors with magnetic impurities [2,3] for which there is creation of bound states in the gap. For the same reasons of symmetry violation, non magnetic impurities act as pair breakers in unconventional superconductors with higher orbital momentum such as d-wave superconductors. As a result, the measured low temperature properties of YBaCu₂O₇ [4] displays a remarkable sensitivity to the presence of non magnetic impurities: the critical temperature, for example, is suppressed even in the lowest order in the disorder potential [5].

Furthermore the d-wave superconductor is special, due to the presence of gap nodes which prevents the complete freezing of scattering processes at low energy.

The standard method to treat these problems of disorder [7,9] combines the T-matrix approximation with standard impurity averaging techniques. For three dimensional systems such as polar superconductors or heavy Fermion superconductors [6] the standard perturbative approach is reliable. In the limit of low impurity concentration n_i , a perturbative expansion in n_i leads to a finite density of states at the chemical potential [8,10].

For two dimensional systems (to which it is believed the high- T_C cuprates belong) the standard procedure of averaging over impurities may be complicated by the appearance of logarithmic singularities in the perturbative expansion of the single electron self-energy [20]. Such a situation appears in a variety of two dimensional systems characterized by a Dirac-like canonical spectrum. In order to control the diagrammatic expansion, all the diagrams with crossing impurity lines would have to be resummed which is technically impossible.

In these systems the existence of a finite density of states induced by disorder is highly controversial [13]. Some non perturbative methods have been used to treat a weak disorder potential [20,21,15]. The solution then depends on the symmetry of the pure system. In the special case of the d-wave superconductor the density of states still vanishes at low energy in the presence of disorder. On the other hand some perturbative self-consistent calculations [11,12] and a non perturbative one [14] show

a finite density of states.

This issue of finite density of states is crucial for the conduction properties in the disordered compound. Indeed, if there exist states in the gap, possible anomalous overlaps between well separated impurities can induce a new conduction mechanism entirely through impurity wave functions in a so-called 'impurity band' [23,24]. This arises the question of localisation.

In this paper, we treat the impurities in the unitary limit (infinite scattering potential V_0), but randomly distributed in space. In this limit each impurity is identical, and create an extended bound state at $E = 0$. These states overlap, but a singular density of states remains at zero energy. Our approach is thus very different from models of random on-site energies considered by others and really does not contradict them.

We introduce a new method to calculate exactly the density of states induced by N non magnetic impurities in a system of two dimensional Dirac fermions in the unitarity limit. We will outline the general features of the proof and present a different derivation than in our previous work [22]. The question of averaging will be discussed in details and we show how the result is exact provide the average over the different configurations of impurities is achieved at the end of the calculation.

Our result can be applied to several systems of Dirac fermions in two dimensions. We review the case of the π -flux phase and explicitly treat the d-wave superconductor.

The generic hamiltonian for a d-wave superconductor can be written

$$H = \sum_{\mathbf{k}} \phi_{\mathbf{k}}^\dagger [\varepsilon_{\mathbf{k}} \sigma_3 + \Delta_{\mathbf{k}} \sigma_1] \phi_{\mathbf{k}}, \quad (1)$$

$$\text{with } \varepsilon_{\mathbf{k}} = W (\cos k_x + \cos k_y) - \mu$$

$$\text{and } \Delta_{\mathbf{k}} = \Delta_0 (\cos k_x - \cos k_y)$$

which describes quasiparticles in the presence of the spin singlet order parameter $\Delta_{\mathbf{k}}$. The σ_i are the Pauli matrices in the particle-hole space and $\phi_{\mathbf{k}}^\dagger = (c_{\mathbf{k},\uparrow}^\dagger, c_{-\mathbf{k},\downarrow})$ is the spinor corresponding to the creation of a particle and a hole. We shall present our results in terms of a

$d_{x^2-y^2}$ state eventhough our conclusions are general for any state where Δ_k vanishes linearly along a direction parallel to the Fermi surface.

Instead of using the Nambu formalism, we work with the diagonalized version of (1) in order to access directly the properties of quasiparticles.

The Bogoliubov transformation gives $c_{\mathbf{k}\uparrow} = u_{\mathbf{k}}\alpha_{\mathbf{k}} - v_{\mathbf{k}}\beta_{\mathbf{k}}$ and $c_{-\mathbf{k}\downarrow}^\dagger = v_{\mathbf{k}}\alpha_{\mathbf{k}} + u_{\mathbf{k}}\beta_{\mathbf{k}}$ where $\alpha_{\mathbf{k}}$ and $\beta_{\mathbf{k}}$ are the annihilation operators for quasiparticle and quasi-hole respectively. The hamiltonian then reads $H = \sum_{\mathbf{k}} \omega_{\mathbf{k}} (\alpha_{\mathbf{k}}^\dagger \alpha_{\mathbf{k}} - \beta_{\mathbf{k}}^\dagger \beta_{\mathbf{k}})$ with $\omega_k = \sqrt{\varepsilon_k^2 + \Delta_k^2}$. The coefficients $u_{\mathbf{k}}$ and $v_{\mathbf{k}}$ satisfy $u_{\mathbf{k}}^2 = 1/2 (1 + \varepsilon_k/\omega_k)$, $v_{\mathbf{k}}^2 = 1/2 (1 - \varepsilon_k/\omega_k)$ and $u_{\mathbf{k}}v_{\mathbf{k}} = \Delta_k/(2\omega_k)$. In order to simplify the calculation, we consider that the spectrum is linearized around the four nodes $(\pm \tilde{k}_F, \pm \tilde{k}_F)$ where close to 1/2 filling, $\tilde{k}_F = (\pi/2 - \mu)$ is close to $\pi/2$.

The disorder is introduced via a scalar scattering potential V_0 located randomly in the system $H_I = V_0 \sum_{i=1}^N c_i^\dagger c_i$, where N is the number of impurities.

The lagrangian density can be written in the general form

$$\mathcal{L}_{\mathbf{k}\mathbf{k}'}^{\alpha\beta} = G_{\mathbf{k}\alpha}^{0-1} \delta_{\alpha\beta} \delta_{\mathbf{k}\mathbf{k}'} - V_0 \sum_{i=1}^N \left(f_{\mathbf{k}\alpha}^{\dagger i} f_{\mathbf{k}'\beta}^i + f_{\mathbf{k}\alpha}^{\prime \dagger i} f_{\mathbf{k}'\beta}^{\prime i} \right), \quad (2)$$

This describes a system of two dimensional Dirac fermions in which N non magnetic impurities located at R_i , $i = 1$ to N , have been introduced as repulsive scalar potentials of strenght V_0 . Quasiparticles with positive energy ($\alpha = 0$) and quasiholes with negative energy ($\alpha = 1$) are described by the bare Green's function $G_{\mathbf{k}\alpha}^{0-1} = i\omega_n - (-1)^\alpha \omega_k$. The factors $f_{\mathbf{k}\alpha}^i$ and $f_{\mathbf{k}\alpha}^{\prime i}$ come from the diagonalization of the initial hamiltonian. Two different terms usually arise from this diagonalization, leading to the sum in eq. (2).

In the case of the d-wave superconductor, we have $f_{\mathbf{k}\alpha}^i = (-1)^\alpha t_{\mathbf{k}\alpha} e^{i\mathbf{k} \cdot \mathbf{R}_i}$ and $f_{\mathbf{k}\alpha}^{\prime i} = t_{\mathbf{k}\alpha} e^{i\mathbf{k} \cdot \mathbf{R}_i}$ where $t_{\mathbf{k},0} = u_{\mathbf{k}}$ and $t_{\mathbf{k},1} = v_{\mathbf{k}}$.

In a previous paper [22] we have studied the case of the π -flux phase, considered as a model for the spin-gap phase of the cuprates [18,19,22]. Following the same diagonalization as exposed in [22], we would get the factors: $f_{\mathbf{k}\alpha}^i = f_{\mathbf{k}\alpha}^{\prime i} = e^{i\mathbf{k} \cdot \mathbf{R}_i}$ if i belongs to sublattice A and $f_{\mathbf{k}\alpha}^i = f_{\mathbf{k}\alpha}^{\prime i} = (-1)^\alpha e^{i\mathbf{k} \cdot \mathbf{R}_i} e^{i\varphi_{\mathbf{k}}}$ if i belongs to sublattice B.

Starting from the lagrangian (2), the equations of motion for the fully dressed Green's function can then be written

$$\sum_{\mathbf{q}\gamma} \mathcal{L}_{\mathbf{k}\mathbf{q}}^{\alpha\gamma} G_{\mathbf{q}\mathbf{k}'}^{\gamma\beta} = \delta_{\mathbf{k}\mathbf{k}'} \delta_{\alpha\beta}. \quad (3)$$

We define $\vec{f}_{\mathbf{k}\alpha}$ and $\vec{g}_{\mathbf{k}'\beta}$ as N components vectors in the space of impurities of components $f_{\mathbf{k}\alpha}^i = u_{\mathbf{k}\alpha} e^{i\mathbf{k} \cdot \mathbf{R}_i}$ and $\mathbf{g}_{\mathbf{k}'\beta}^i = \sum_{\mathbf{q}\gamma} f_{\mathbf{q}\gamma}^i G_{\mathbf{q}\mathbf{k}'}^{\gamma\beta}$ and respectively for $\vec{f}_{\mathbf{k}\alpha}'$ and $\vec{g}_{\mathbf{k}'\beta}'$.

The Dyson equation (without any impurity averaging) can be written as:

$$G_{\mathbf{k}\mathbf{k}'}^{\alpha\beta} = G_{\mathbf{k}\alpha}^0 \delta_{\mathbf{k}\mathbf{k}'} \delta_{\alpha\beta} + V_0 G_{\mathbf{k}\alpha}^0 \left(\vec{f}_{\mathbf{k}\alpha}^\dagger \cdot \vec{g}_{\mathbf{k}'\beta} + \vec{f}_{\mathbf{k}\alpha}'^\dagger \cdot \vec{g}_{\mathbf{k}'\beta}' \right), \quad (4)$$

where the scalar product in the parentheses runs over the positions of impurities.

Solving with respect to $\vec{g}$ and $\vec{g}'$ gives

$$\hat{M} \begin{pmatrix} \vec{g} \\ \vec{g}' \end{pmatrix} = \begin{pmatrix} G^0 \vec{f} \\ G^0 \vec{f}' \end{pmatrix}, \quad (5)$$

$$\text{where } \hat{M} = \begin{pmatrix} \hat{I} + \hat{A} & \hat{B} \\ \hat{B} & \hat{I} + \hat{A} \end{pmatrix};$$

$$\hat{A}_{ij} = \sum_{\mathbf{k}\alpha} G_{\mathbf{k}\alpha}^0 f_{\mathbf{k}\alpha}^{\dagger i} f_{\mathbf{k}\alpha}^i$$

$$\text{and } \hat{B}_{ij} = \sum_{\mathbf{k}\alpha} G_{\mathbf{k}\alpha}^0 f_{\mathbf{k}\alpha}^{\prime \dagger i} f_{\mathbf{k}\alpha}^{\prime i} (R_j).$$

We thus get the T-matrix equation

$$G_{\mathbf{k}\mathbf{k}'}^{\alpha\beta} = G_{\mathbf{k}\alpha}^0 \delta_{\mathbf{k}\mathbf{k}'} \delta_{\alpha\beta} + G_{\mathbf{k}\alpha}^0 \begin{pmatrix} \vec{f}_{\mathbf{k}\alpha} & \vec{f}_{\mathbf{k}\alpha}' \end{pmatrix} \hat{T} \begin{pmatrix} \vec{f}_{\mathbf{k}'\beta} \\ \vec{f}_{\mathbf{k}'\beta}' \end{pmatrix} G_{\mathbf{k}'\beta}^0, \quad (6)$$

with $\hat{T} = -V_0 \hat{M}^{-1}$.

The additional density of states is given by $\delta\rho = -1/\pi \text{Im} \sum_{\mathbf{k}\alpha} \delta G_{\mathbf{k}\mathbf{k}}^{\alpha\alpha}$. Using the equality $\partial \hat{G}^0 / \partial i\omega_n = \hat{G}^0{}^2$ and the cyclicity of the trace we get $\delta\rho(\omega) = -1/\pi \text{Im} \text{Tr} \left(\hat{M}^{-1} \partial \hat{M} / \partial i\omega_n \right)$. The trace is over the positions of impurities.

In our previous study [22] we solved the problem by writing the term in the brackets as the derivative of a logarithm and evaluating the resulting determinant. Here we use another trick which consists in using the form of $\hat{M}^2$ to factorise the logarithmic divergence characteristic of these problems. This derivation will make clear the question of averaging on disorder. We thus write

$$\delta\rho(\omega) = \frac{-1}{2\pi} \text{Im} \text{Tr} \left[\hat{M}^{-2} \partial \hat{M}^2 / \partial i\omega_n \right] \quad (7)$$

and carefully study the form of $\hat{M}^2$.

The solution of the problem depends on the actual form of M_{ij} .

As for the π -flux phase, we can show that $M_{ij} \approx 1/R_{ij}$. This fact was previously acknowledged by other others [23,25] who found an overall factor of the order of $(\Delta_0/W)1/R_{ij}$.

Let's first consider the case of symmetric bandwidths for positive and negative energies. This means we are at half filling for the superconductor ($\mu = 0$). We show below how this $1/R$ value arises in the case where $W = \Delta_0$.

We get

$$A_{ij} = \sum_{\mathbf{k} \in BZ} \frac{u_{\mathbf{k}}^2 e^{i\mathbf{k} \cdot \mathbf{R}_{ij}}}{i\omega_n - \omega_{\mathbf{k}}} + \sum_{\mathbf{k} \in BZ} \frac{v_{\mathbf{k}}^2 e^{i\mathbf{k} \cdot \mathbf{R}_{ij}}}{i\omega_n + \omega_{\mathbf{k}}}$$

so that

$$A_{ij} = \sum_{\mathbf{k} \in BZ} \frac{i\omega_n e^{i\mathbf{k} \cdot \mathbf{R}_{ij}}}{i\omega_n - \omega_{\mathbf{k}}} + \sum_{\mathbf{k} \in BZ} \frac{\varepsilon_{\mathbf{k}} e^{i\mathbf{k} \cdot \mathbf{R}_{ij}}}{i\omega_n + \omega_{\mathbf{k}}} \\ = 2\pi \mathcal{F}^0(R_{ij}) \frac{\omega}{\Delta_0^2} \ln \left| \frac{\omega}{\Delta_0} \right| + \frac{2i\pi}{R_{ij}} \mathcal{F}^1(R_{ij}), \quad (8)$$

with $\mathcal{F}^0(R) = 2 \left[\cos \frac{\pi}{2}(R_x + R_y) + \cos \frac{\pi}{2}(R_x - R_y) \right]$ and

$$\mathcal{F}^1(R) = 2 \left[\sin \frac{\pi}{2}(R_x + R_y) (\cos \varphi + \sin \varphi) \right. \\ \left. + \sin \frac{\pi}{2}(R_x - R_y) (\cos \varphi - \sin \varphi) \right],$$

where φ is the angle between $\mathbf{R}$ and the $\vec{x}$ axis.

For $\hat{B}$ we write

$$B_{ij} = \sum_{\mathbf{k} \in BZ} \frac{u_{\mathbf{k}} v_{\mathbf{k}} e^{i\mathbf{k} \cdot \mathbf{R}_{ij}}}{i\omega_n - \omega_{\mathbf{k}}} + \sum_{\mathbf{k} \in BZ} \frac{u_{\mathbf{k}} v_{\mathbf{k}} e^{i\mathbf{k} \cdot \mathbf{R}_{ij}}}{i\omega_n + \omega_{\mathbf{k}}}$$

so that we find

$$B_{ij} = \frac{2i\pi}{R_{ij}} \mathcal{F}^2(R_{ij}), \quad (9)$$

with

$$\mathcal{F}^2(R) = 2 \left[\sin \frac{\pi}{2}(R_x + R_y) (\cos \varphi - \sin \varphi) \right. \\ \left. + \sin \frac{\pi}{2}(R_x - R_y) (\cos \varphi + \sin \varphi) \right].$$

The key point in the evaluation of the density of states is that $\hat{M}^2$ shows a logarithmic divergence.

We factorize explicitly this divergence by taking

$$\hat{M}^2 = \ln \left| \frac{\Delta_0}{\omega_n} \right| \hat{S} \quad (10)$$

where $\hat{S}$ is a matrix which depends on the particular configuration of impurities we work with. Two terms emerge in the density of states:

$$\delta\rho(\omega) = \frac{-1}{\pi} \text{Im} \text{Tr} \left[\ln^{-1} \left| \frac{\omega_n}{\Delta_0} \right| \frac{\partial \ln |\omega_n/\Delta_0|}{\partial \omega} \hat{I} + \hat{S}^{-1} \frac{\partial \hat{S}}{\partial i\omega_n} \right]. \quad (11)$$

Note that the first term doesn't depend on the particular configuration of impurities. The average over disorder will act only on the second term. After analytic continuation, we find per unit of volume

$$\delta\rho(\omega) = \frac{n_i}{\omega (\ln^2 |\omega/\Delta_0| + (\pi/2)^2)} - \frac{2}{\pi V} \text{Im} \left\langle \text{Tr} \hat{S}^{-1} \frac{\partial \hat{S}}{\partial \omega} \right\rangle, \quad (12)$$

where the brackets denote the average over disorder.

We argue now that the contribution coming from $\hat{S}$ is negligible. For this purpose, we make an overestimate of $\hat{S}$ with the $N/2 \times N/2$ matrix $\hat{S}^a$ satisfying $S_{ij}^a = 1$ if $R_{ij} < \Delta_0/|\omega_n|$ and 0 elsewhere. In this approximation we have overevaluated the long distance interactions between impurities by replacing the slow decay of S_{ij} which vanishes at $R_{ij} = |\Delta_0/i\omega_n|$ by a step function with a cut-off at $R_{ij} = |D/i\omega_n|$. This special form of $\hat{S}$ thus leads to an upper bound for the averaged second term in (12). Our aim is now to prove that it is negligible as compared to the first term. $\partial \hat{S}^a / \partial \omega$ is then the matrix which elements $\partial S^a / \partial \omega|_{ij}$ vanish everywhere except on the external boundary of the circle of radius $R_{ij} = |\Delta_0/\omega_n|$.

The main difficulty in the inversion of $\hat{S}^a$ is that two circles of radius $\Delta_0/|\omega_n|$ centered around two points i and j very close to each other will overlap, leading to the same number of non zero coefficients in the lines i and j of $\hat{S}^a$. In order to differentiate the sums $\sum_{\mathbf{k}} S_{ik}^a S_{kj}^{a-1}$ and $\sum_{\mathbf{k}} S_{ik}^a S_{kj}^{a-1}$ we have thus used the external boundary of the circle to compensate its volume in $\hat{S}^a$.

We take $\hat{S}_{ij}^{a-1} = (|\omega_n|/(\sqrt{\pi}\Delta_0)) U_{ij}$. For all j inside a circle of radius $\Delta_0/|\omega_n|$ around the point i , U_{ij} is a random configuration of ± 1 so that $\sum_j U_{ij} \sim \sqrt{\pi}\Delta_0/|\omega_n|$. In addition all the points j situated in the external boundary of this circle have $U_{ij} = -1/(2\sqrt{\pi})$. Elsewhere $U_{ij} = 0$.

We thus get $\hat{S}^{a-1} (\partial \hat{S}^a / \partial \omega) = \sqrt{\pi}$ which is negligible as compared to the first term. Thus this term is of second order as compared to the first term in (12).

Provided $\hat{M}^2$ displays a logarithmic divergence, we can factorize this divergence and show that the exact density of state in the unitarity limit and in the limit of low frequencies is

$$\delta\rho(\omega) \simeq \frac{n_i}{|\omega| (\ln^2 |\omega/\Delta_0| + (\pi/2)^2)}. \quad (13)$$

In the case where $\Delta_0 \neq W$ the logarithmic singularity gets an overall prefactor Δ_0/W [23] which leads to the most general form at low energy

$$\delta\rho(\omega) \simeq \frac{\Delta_0}{W} \frac{n_i}{|\omega| (\ln^2 |\omega/\Delta_0| + (\pi/2)^2)}. \quad (14)$$

The equation (14) is thus the most general expression for the density of states induced by non-magnetic impurities in the unitarity limit, and for energy bands symmetric for positive and negative energies.

Note that this expression is normalisable. If the impurities were totally uncorrelated, we would find N δ -functions at $\omega = 0$. Here we see clearly the overlap of impurity states which leads to a broadening of the δ functions. The interacting states repeal each other, but not enough to kill the divergence. This level repulsion was found by other methods [20] for Dirac fermions in two dimensions in presence of disorder, but away from unitarity limit.

What happens if the bandwidths are not symmetric anymore, that is if $\mu \neq 0$ but still $\mu \ll \Delta_0$?

First the nodes are moved away from the point $(\pm\pi/2, \pm\pi/2)$ so that transversal nodes are now separated by the vectors $\mathbf{Q} = (\pi(1-\delta), \pi(1-\delta))$ and $\mathbf{Q}^* = (-\pi(1-\delta), \pi(1-\delta))$ where $\delta = \mu/\Delta_0$ and μ is the increase in the chemical potential. This leads to a change of the phase factors in A_{ij} and B_{ij} . Namely we get $\mathcal{F}^0(R) = 2 [\cos(\mathbf{Q} \cdot \mathbf{R}/2) + \cos(\mathbf{Q}^* \cdot \mathbf{R}/2)]$;

$$\mathcal{F}^1(R) = 2 [\sin(\mathbf{Q} \cdot \mathbf{R}/2) (\cos \varphi + \sin \varphi) - \sin(\mathbf{Q}^* \cdot \mathbf{R}/2) (\cos \varphi - \sin \varphi)] ,$$

and

$$\mathcal{F}^2(R) = 2 [\sin(\mathbf{Q} \cdot \mathbf{R}/2) (\cos \varphi - \sin \varphi) - \sin(\mathbf{Q}^* \cdot \mathbf{R}/2) (\cos \varphi + \sin \varphi)] .$$

As δ is a small parameter, this change in the phase won't affect the existence of the logarithmic divergence in $\hat{M}^2$.

More importantly, away from half filling, the bands of quasi particles and quasi holes become asymmetric to account for the removing of particles in the system. This gives additional terms in A_{ij} and B_{ij} of the form $\sum_{1 < |k| < 1+\delta} e^{i\mathbf{k} \cdot \mathbf{R}} / (i\omega_n - \omega_k)$. We show that [26] their contribution in $\hat{M}_{ij}^2$ is of order of $\delta J_0(R_{ij})/\Delta_0^2$ where J_0 is the Bessel function of rank zero. This doesn't affect the logarithmic divergence at low energies.

The density of states is thus stable with respect to a small perturbation of the chemical potential.

The result (14) holds for any system of Dirac fermions in two dimensions, provided the hopping matrix between impurities goes like $1/R_{ij}$. Thus it seems to be generic for two dimensional Dirac fermions in presence of Poissonian disorder. Indeed the same result as (14) has been obtained for a system of electrons in a strong magnetic field in two dimensions, when the disorder is Poissonian [27].

This result has to be compared with one dimensional spin-Peierls and two-leg ladder compounds for which non magnetic impurities create a Dyson-like singularity $\delta\rho(\omega) \sim 1/(|\omega| \ln^3 |\omega/D|)$ [16,17]. In one dimension, the Dyson singularity is a signature of delocalised states in the system: there is a direct relation between the localisation length and the density of states [28] which shows the divergence of the localisation length at low energies. In two dimensions this theorem doesn't hold anymore and the question of localisation is still open.

We would like to thank A. M. Tsvelik, R. Joynt, M. H. Hettler, A.V. Balatsky, P. Coleman and J. Chalker for useful discussions related to this work.

This work is supported by NSF Grant No. DMR-9523361 and by (CP) a Bourse Lavoisier.

- [3] T. Tsuneto, Prog. Theor. Phys. **28**, 857 (1962); D. Maskowitz and L. P. Kadanoff, Phys. Rev. **131**, 563 (1963).
- [4] K. Ishida *et al.*, Physica C **185**, 1115 (1991).
- [5] H. Alloul *et al.*, Phys. Rev. Lett. **67**, 3140 (1991).
- [6] M. Sigrist and K. Ueda, Rev. Mod. Phys. **64**, 239 (1991).
- [7] P.J. Hirshfeld, P. Wölfle and D. Einzel, Phys. Rev. B **37**, 83 (1988).
- [8] L. P. Gorkov and P. A. Kalugin, JETP Lett. **41**, 253 (1985).
- [9] P. A. Lee and T. V. Ramakrishnan, Rev. Mod. Phys. **57**, 287 (1985).
- [10] K. Ueda and T. M. Rice, in *Theory of Heavy Fermions and Valence Fluctuations*, (Springer, Berlin, 1985) p. 267.
- [11] Y. Hatsugai and P. A. Lee, Phys. Rev. B **48**, 4204 (1993).
- [12] D-H. Lee and Z. Wang, Phil. Mag. Lett. **73**, 145 (1995).
- [13] R. Joynt, J. Low Temp. Phys. **109**, 811 (1997).
- [14] K. Ziegler, M. H. Hettler and P. J. Hirshfeld, Phys. Rev. Lett., **77**, 3013 (1996).
- [15] A. A. Nersesyan and A. M. Tsvelik, Phys. Rev. Lett. **78**, 3982 (1997).
- [16] D. G. Shelton and A. M. Tsvelik, Phys. Rev. B **57**, 14242 (1998); A. O. Gogolin *et al.* cond-mat/ 9707341.
- [17] F.J. Dyson, Phys. Rev. **92**, 1331 (1953).
- [18] N. Nagaosa and T.K Ng, Phys. Rev. B **51**, 15588 (1995).
- [19] S. Krivenko and G. Khaliullin, JETP Lett. **62**, 723 (1995); G. Khaliullin *et al.* Phys. Rev. B **56**, 11882 (1997).
- [20] A.A. Nersesyan *et al.*, Phys. Rev. Lett. **72**, 2628 (1994); A.A Nersesyan, A. M. Tsvelik and F. Wenger, Nucl. Phys. B **438**, 561 (1995).
- [21] C. Mudry *et al.*, Nucl. Phys. B **446**, 382 (1996).
- [22] C. Pépin and P. A. Lee, Phys. Rev. Lett. **81**, 2779 (1998).
- [23] A. V. Balatsky and M. I. Salkola, Phys. Rev. Lett. **76** 2386 (1996); A. V. Balatsky *et al.*, Phys. Rev. B **51**, 1547 (1995).
- [24] P. A. Lee, Phys. Rev. Lett. **71**, 1887 (1993).
- [25] D. N. Aristov and A. G. Yashenkin, Phys. Rev. Lett. **80**, 1116 (1998).
- [26] These terms take for example the following form $\sum_l \sum_{1 < |k_1| < 1+\delta} \frac{e^{i\mathbf{k}_1 \cdot \mathbf{R}_{il}}}{i\omega_n - \Delta_0 k_1} \sum_{\mathbf{k}_2} \frac{e^{i\mathbf{k}_2 \cdot \mathbf{R}_{lj}}}{i\omega_n - \Delta_0 k_2}$. By summing first over the points l we get the result.
- [27] E. Brézin, D.J. Gross and C. Itzykson, Nucl. Phys. B **235** (1984), 24-44.
- [28] D. J. Thouless, J. Phys. C **5**, 77 (1972).

[1] P. W. Anderson, Phys. Rev. Lett. **3**, 325 (1955).

[2] A. A. Abrikosov and L.P. Gorkov, JETP **12**, 1243 (1961).